

PROSAT Meltblown Polypropylene Wipes

Presaturated with 91% IPA and 9% DI water

Manufactured from meltblown polypropylene these PROSAT presaturated wipes offer exceptional cleanliness. They are low in nonvolatile residues as well as particles and fibres. The use of presaturated wipes provides maximum process control.

Saturated with a blend of 91% isopropyl alcohol and 9% deionized water these wipes are an excellent choice for general surface cleaning where fast drying times are desired. The use of presaturated wipes reduces VOC emissions and solvent use up to 35% over spraying. The wipes are provided in convenient and easy to use peel and reseal pouches



Features	Benefits
Presaturated with 91% isopropyl alcohol and 9% deionized water	<ul style="list-style-type: none">• Excellent choice when fast drying times are required
Low in nonvolatile residue as well as particles and fibres	<ul style="list-style-type: none">• Ideal for multiple applications
Resealable pouch	<ul style="list-style-type: none">• Preserves cleanliness and solvent saturation levels

Part No.	Description	Size	Packaging
PS-919	PROSAT Meltblown Polypropylene Wipes Presaturated with 91% IPA 9% DI Water	230 x 280 mm	30 per pouch / 50 pouches per case

Product Information	
Material	100% polypropylene
Construction	Meltblown nonwoven
Environment	ISO 5-8 Grade C/D



Technical Data		
Attribute (units)	Typical Value	Test Method
Basis weight, nominal; (g/m ²)	36	Contec Method
Non-volatile residue, NVR		IENT-RP-CC004.3, Sec. 6.1.2
In deionized water; (g/m ²)	0.011	
In isopropyl alcohol; (g/m ²)	0.070	
Specific ions		IENT-RP-CC004.3, Sec. 6.2.2
Sodium; (ppm)	3.0	
Chloride; (ppm)	5.0	
Particles, readily releasable		IENT-RP-CC004.2, Sec. 5.1
Particles ≥ 0.5µm; (x10 ⁶ /m ²)	19.7	
Fibres ≥ 100µm; (x 10 ³ /m ²)	6.3	IENT-RP-CC004.2, Sec. 5.2



Notes

- The data shown are typical values and should not be used as product specifications.
- Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- Current and/or comparison data may be available. Please contact a Contec sales representative for details.

Test Methods

- CTM = Contec Test Method
- IENT-RP-CC004.3 = Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of environmental Sciences and Technology, Rolling Meadows IL.

Packaging

Packaging Materials				
Outer bags	Low density polyethylene (LDPE) 			
Case	Corrugated fibreboard (PAP) 			
Packaging Configuration	EA/PCH	PCH/OB1	OB1/CS	EA/CS
PS-919	30	10	5	1,500

EA = Each; OB1 = Outer Bag 1; PCH = Pouch; CS = Case

Recycle Key

PET	
LDPE	
PAP	

For more information or to request a sample,
email infoeu@contecinc.com or phone +33 (0) 2 97 43 76 98.

PDSW042_EMEA | 031025

Copyright © 2025 Contec, Inc. All rights reserved.

Contact us:
infoeu@contecinc.com
contecinc.com/eu

Vannes
France
tel: +33(0) 2 97 43 76 98

Spartanburg, SC
United States
tel: +1 (864) 503-8333

 **CONTEC**
CLEANROOM