

# Polynit Wipes

## 100% no-run interlock knit polyester wipe with knife cut edges

Polynit Wipes are made of 100% knitted textured polyester with knife cut edges for a very soft wipe. The soft edge is ideal for use on surfaces which are vulnerable to scratching. Polyester wipes are chemically resistant and exceptionally low in particles and fibres. An interlock knit creates a durable fabric, the addition of a periodic additional stitch of a no-run interlock knit prevents the fabric unraveling creating an even more durable fabric with strong edges.

The wipes are laundered and packaged in a cleanroom. They have good sorbency with solvents and are abrasion and chemical resistant.

A validated sterile version is available.




Features	Benefits
Laundered knitted 100% polyester fabric	<ul style="list-style-type: none"><li>Extremely low levels of particles and fibers</li></ul>
Soft edge	<ul style="list-style-type: none"><li>Ideal for use on surfaces which are vulnerable to scratching</li></ul>
100% knitted polyester	<ul style="list-style-type: none"><li>Makes it compatible with many solvents</li></ul>

Part No.	Description	Size	Packaging
PN-44	Polynit Wipes Flat stacked	102 x 102 mm	300 per bag / 16 bags per case
PN-44B	Polynit Wipes Bulk	102 x 102 mm	600 per bag / 8 bags per case
PN-99	Polynit Wipes Flat stacked	230 x 230 mm	75 per bag / 16 bags per case
PN-99 B	Polynit Wipes Bulk	230 x 230 mm	300 per bag / 4 bags per case
PN-99B/150	Polynit Wipes Bulk	230 x 230 mm	150 per bag / 8 bags per case
PN-1212	Polynit Wipes Flat stacked	305 x 305 mm	75 per bag / 10 bags per case
PN-1212B	Polynit Wipes Bulk	305 x 305 mm	150 per bag / 4 bags per case

### Product Information

Material	100% polyester
Construction	Interlock knit
Environment	ISO 3-8 Grade C/D



Technical Data			
	PN-99B, PN-99B/150, PN-1212B	PN-44, PN-44B, PN- 99, PN-1212	
Attribute (units)	Typical Value	Typical Value	Test Method
Basis weight, nominal; (g/m <sup>2</sup> )	140	140	Contec Method
Sorbent capacity; (mL/m <sup>2</sup> )	369	357	IEST-RP-CC004.3, Sec. 8.1
Sorptive rate; (seconds)	<1	<1	
Non-volatile residue, NVR			IEST-RP-CC004.3, Sec. 7.1.2
In deionized water; (g/m <sup>2</sup> )	0.007	0.003	
In isopropyl alcohol; (g/m <sup>2</sup> )	0.011	0.018	
Specific ions			IEST-RP-CC004.3, Sec. 7.2.2
Sodium; (ppm)	0.157	0.119	
Chloride; (ppm)	0.126	0.042	
Particles, readily releasable			IEST-RP-CC004.2, Sec. 5.1
Particles $\geq 0.5\mu\text{m}$ ; (x10 <sup>6</sup> /m <sup>2</sup> )	1.52	6.9	
Fibres $\geq 100\mu\text{m}$ ; (x 10 <sup>3</sup> /m <sup>2</sup> )	0.766	0.53	

## Notes

- a) The data shown are typical values and should not be used as product specifications.
- b) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- c) Current and/or comparison data may be available. Please contact a Contec sales representative for details.

## Test Methods

1. CTM = Contec Test Method
2. IEST-RP-CC004.3 = Evaluating Wiping Materials Used in Cleanroom and Other Controlled Environments, Institute of Environmental Sciences and Technology, Rolling Meadows IL.

## Packaging

Packaging Materials				
Outer bags	Low density polyethylene (LDPE) 			
Case	Corrugated fibreboard (PAP) 			
Packaging Configuration	EA/OB1	OB1/OB2	OB2/CS	EA/CS
PN-44	300	1	16	4,800
PN-44B	600	1	8	4,800
PN-99	75	2	8	1,200
PN-99B	300	1	4	1,200
PN-99B/150	150	1	8	1,200
PN-1212	75	1	10	750
PN-1212B	150	1	4	600

EA = Each; OB1 = Outer Bag 1; OB2 = Outer Bag 2; CS = Case

## Recycle Key

PET	
LDPE	
PAP	

For more information or to request a sample,  
email [infoeu@contecinc.com](mailto:infoeu@contecinc.com) or phone +33 (0) 2 97 43 76 98.

PDSW075\_EMEA | 201025

Copyright © 2025 Contec, Inc. All rights reserved.

Contact us:  
[infoeu@contecinc.com](mailto:infoeu@contecinc.com)  
[contecinc.com/eu](http://contecinc.com/eu)

Vannes  
France  
tel: +33(0) 2 97 43 76 98

Spartanburg, SC  
United States  
tel: +1 (864) 503-8333

 **CONTEC**<sup>®</sup>  
CLEANROOM